


High Efficiency Low LID Mono PERC with Half-cut Technology



Complete System and Product Certifications

IEC 61215, IEC61730, UL1703

ISO 9001:2008: ISO Quality Management System

ISO 14001: 2004: ISO Environment Management System

TS62941: Guideline for module design qualification and type approval OHSAS 18001: 2007 Occupational Health and Safety







* Specifications subject to technical changes and tests. LONGi Solar reserves the right of interpretation.

Positive power tolerance (0 $^{\sim}$ +5W) guaranteed

High module conversion efficiency (up to 19.5%)

Slower power degradation enabled by Low LID Mono PERC technology: first year <2%, 0.55% year 2-25

Solid PID resistance ensured by solar cell process optimization and careful module BOM selection

Reduced resistive loss with lower operating current

Higher energy yield with lower operating temperature


 $\textbf{Reduced hot spot risk} \ \text{with optimized electrical design and lower operating current}$



Note: Due to continuous technical innovation, R&D and improvement, technical data above mentioned may be of modification accordingly. LONGi Solar have the sole right to make such modification at anytime without further notice; Demanding party shall request for the latest datasheet for such as contract need, and make it a consisting and binding part of lawful documentation duly signed by both parties.

LR4-60HPB **345~365M**

Design (mm) Mechanical Parameters Operating Parameters



Cell Orientation: 120 (6×20)

Junction Box: IP68, three diodes

Output Cable: 4mm², 300mm in length
length can be customized

Glass: Single glass

3.2mm coated tempered glass

Frame: Anodized aluminum alloy frame

Units: mm(inch)
Tolerance:
Length: ±2mm
Widfn: ±2mm
Relght: ±1mm
Pitch-row: ±1mm

Tolerance:
180pcs per 20'GP

Helght: ±1mm
Pitch-row: ±1mm

Weight: 20kg

Operational Temperature: -40 C $^{\sim}$ +85 C Power Output Tolerance: 0 $^{\sim}$ +5 W Voc and Isc Tolerance: $\pm 3\%$ Maximum System Voltage: DC1000V (IEC/UL) Maximum Series Fuse Rating: 20A Nominal Operating Cell Temperature: 45 ± 2 C Safety Class: Class II

Fire Rating: UL type 1 or type 2


Electrical Characteristics Test uncertainty for Pmax: ±3%											
Model Number	LR4-60⊦	LR4-60HPB-345M		LR4-60HPB-350M		LR4-60HPB-355M		LR4-60HPB-360M		LR4-60HPB-365M	
Testing Condition	STC	NOCT	STC	NOCT	STC	NOCT	STC	NOCT	STC	NOCT	
Maximum Power (Pmax/W)	345	255.6	350	259.3	355	263.0	360	266.7	365	270.4	
Open Circuit Voltage (Voc/V)	40.3	37.6	40.5	37.8	40.7	38.0	40.9	38.2	41.1	38.4	
Short Circuit Current (Isc/A)	10.93	8.81	11.02	8.89	11.10	8.95	11.20	9.03	11.28	9.09	
Voltage at Maximum Power (Vmp/V)	33.1	30.6	33.3	30.8	33.5	30.9	33.7	31.1	33.9	31.3	
Current at Maximum Power (Imp/A)	10.43	8.36	10.52	8.44	10.60	8.50	10.69	8.57	10.77	8.64	
Module Efficiency(%)	18	18.5		18.7		19.0		19.3		19.5	
STC (Standard Testing Conditions): Irradiance 1000W/m², Cell Temperature 25°C, Spectra at AM1.5											

NOCT (Nominal Operating Cell Temperature): Irradiance 800W/m², Ambient Temperature 20 °C, Spectra at AM1.5, Wind at 1m/S


Temperature Ratings (STC)		Mechanical Loading					
Temperature Coefficient of Isc	+0.057%/°C	Front Side Maximum Static Loading	5400Pa				
Temperature Coefficient of Voc	-0.286%/ °C	Rear Side Maximum Static Loading	2400Pa				
Temperature Coefficient of Pmax	-0.370%/°C	Hailstone Test	25mm Hailstone at the speed of 23m/s				

I-V Curve


Current-Voltage Curve (LR4-60HPB-355M)



Power-Voltage Curve (LR4-60HPB-355M)



Current-Voltage Curve (LR4-60HPB-355M)





Room 801, Tower 3, Lujiazui Financial Plaza, No.826 Century Avenue, Pudong Shanghai, 200120, China Tel: +86-21-80162606 E-mail: module@longi-silicon.com Facebook: www.facebook.com/LONGi Solar

Note: Due to continuous technical innovation, R&D and improvement, technical data above mentioned may be of modification accordingly. LONGi Solar have the sole right to make such modification at anytime without further notice; Demanding party shall request for the latest datasheet for such as contract need, and make it a consisting and binding part of lawful documentation duly signed by both parties.